

Honeywell A-C® Performance Additives

Typical Properties

	Mettler Drop Point (ASTM D-3954)		Hardness, dmm (ASTM D-5)	Density, g/cc (ASTM D-1505)	Viscosity cps, @140°C (Brookfield)	Acid Number, mg KOH/g (ASTM D-1386)	Physical Form
Polyethylene Homopolymers							
A-C 820A ⁽¹⁾	126°C	259°F	1.0	0.97	80	Nil	Powder
A-C 1810A ⁽¹⁾	121°C	250°F	< 2.0	0.95	19	Nil	Powder
A-C 9, 9A, 9F	115°C	239°F	0.5	0.93	450	Nil	Prill, Powder, Fine Powder
A-C 8, 8A	113°C	235°F	1.0	0.93	450	Nil	Prill, Powder
A-C 3A	112°C	234°F	2.0	0.92	450	Nil	Powder
A-C 725	110°C	230°F	3.5	0.92	1,400	Nil	Diced
A-C 735	110°C	230°F	2.5	0.92	6,000	Nil	Diced
A-C 715	109°C	228°F	2.5	0.92	4,000	Nil	Diced
A-C 7, 7A	109°C	228°F	2.5	0.92	450	Nil	Prill, Powder
A-C 6, 6A	106°C	223°F	4.0	0.92	375	Nil	Prill, Powder
A-C 16 ⁽⁶⁾ , 16A	102°C	216°F	5.5	0.91	525	Nil	Prill, Powder
A-C 617, 617A	101°C	214°F	7.0	0.91	180	Nil	Prill, Powder
A-C 1702 ⁽²⁾	90°C	194°F	98 ⁽³⁾	0.88	30	Nil	Grease-like
Oxidized Polyethylene Homopolymers							
A-C 673P	110°C	230°F	<1.0	0.95	400	17	Pastille
A-C 680	108°C	226°F	1.5	0.93	250	16	Prill
A-C 655	107°C	225°F	2.5	0.93	210	16	Prill
A-C 629, 629A	101°C	214°F	5.5	0.93	200	15	Prill, Powder
A-C 656	98°C	208°F	9.0	0.92	185	15	Prill
A-C 6702 ⁽⁵⁾	88°C	190°F	90 ⁽³⁾	0.85	35	15	Grease-like
High-Density Oxidized Polyethylene Homopolymers							
A-C 307, 307A	140°C	284°F	<0.5	0.98	85,000 @150°C	7	Granule, Powder
A-C 316, 316A	140°C	284°F	<0.5	0.98	8,500 @150°C	16	Granule, Powder
A-C 325	136°C	277°F	<0.5	0.99	4,500 @150°C	25	Granule
A-C 392	138°C	280°F	<0.5	0.99	4,500 @150°C	30	Granule
A-C 330	137°C	279°F	<0.5	0.99	3,600 @150°C	30	Granule
A-C 395, 395A	137°C	279°F	<0.5	1.00	2,500 @150°C	41	Granule, Powder
Polypropylene Homopolymers							
	Softening Point						
A-C 1754	167°C	333°F	<0.5	0.89	775 @190°C	Nil	Powder
A-C 1660	150°C	302°F	<0.5	0.89	60 @190°C	Nil	Powder
A-C 1089	146°C	295°F	<0.5	0.91	45 @190°C	Nil	Powder
Ethylene-Acrylic Acid Copolymers							
A-C 540, 540A	105°C	221°F	2.0	0.93	575	40	Prill, Powder
A-C 580	95°C	203°F	4.0	0.93	650	75	Prill
A-C 5120 ⁽⁶⁾	92°C	198°F	8.0	0.93	600	120	Prill

Honeywell A-C® Performance Additives

Typical Properties

	Mettler Drop Point (ASTM D-3954)	Hardness, dmm (ASTM D-5)	Density, g/cc (ASTM D-1505)	Viscosity cps, @140°C (Brookfield)	Acid Number, mg KOH/g (ASTM D-1386)	Physical Form
--	-------------------------------------	-----------------------------	--------------------------------	--	---	------------------

Ethylene-Vinyl Acetate Copolymers

A-C 405T	102°C 216°F	4.0	0.92	600	6% Vinyl Acetate	Prill
A-C 405M	100°C 212°F	5.0	0.92	600	8.5% Vinyl Acetate	Prill
A-C 405S	94°C 201°F	7.0	0.92	600	10.5% Vinyl Acetate	Prill
A-C 400, 400A	92°C 198°F	9.5	0.92	595	13% Vinyl Acetate	Prill, Powder
A-C 415	89°C 192°F	12.5	0.92	1,300	15% Vinyl Acetate	Prill
A-C 430 ⁽⁶⁾	75°C 167°F	70 ⁽⁷⁾	0.93	600	26% Vinyl Acetate	Tacky solid

Oxidized Ethylene-Vinyl Acetate Copolymers

A-C 645 P	99°C 210°F	5.0	0.94	375	13 (SAP=56)	Pastille
-----------	------------	-----	------	-----	-------------	----------

	Melt. Point (DSC)	Cation Type	Viscosity cps, @190°C (Brookfield)	Acid Number, mg KOH/g (ASTM D-1386)	Physical Form
--	----------------------	----------------	--	---	------------------

AClyn® Low Molecular Weight Ionomers

AClyn 201 ⁽⁶⁾ , 201A ⁽⁶⁾	102°C 215°F	Ca	5,500	42	Granular, Powder
AClyn 295, 295A ⁽⁶⁾	99°C 210°F	Zn	4,500	Nil	Granular, Powder
AClyn 285 ⁽⁶⁾ , 285A ⁽⁶⁾	82°C 180°F	Na	80,000	20	Granular, Powder

	Mettler Drop Point (ASTM D-3954)	Hardness, dmm (ASTM D-5)	Density, g/cc (ASTM D-1505)	Viscosity cps, @140°C (Brookfield)	Saponification# mg KOH/g	% MAH Bound	Bound SAP# mg KOH/g	Physical Form
--	--	--------------------------------	-----------------------------------	--	-----------------------------	----------------	---------------------------	------------------

Ethylene Maleic Anhydride Copolymers

A-C 573A, 573P	106°C 223°F	4.5	0.92	600	5	95+%	5	Powder, Pastille
----------------	-------------	-----	------	-----	---	------	---	------------------

Propylene Maleic Anhydride Copolymers

	Softening Point								
A-C 907P	152°C	306°F	<0.5	0.93	350 @190°C	87	70%	60	Pastille
A-C 596A, 596P	141°C	286°F	<0.5	0.93	150 @190°C	50	85%	43	Powder, Pastille
A-C 950P	149°C	300°F	<0.5	0.93	2,000 @190°C	50	65%	33	Pastille
A-C 1325P	149°C	300°F	<0.5	0.92	1,600 @190°C	18	78%	14	Pastille

Notes:

- (1) Product only available as a powder
 (2) Product only available in fiber drums or slabs
 (3) Product has a grease-like consistency, hardness ASTM D-1321
 (4) Product only available in steel drums
 (5) Product only available in fiber or steel drums
 (6) Product only available in fiber drums
 (7) Product is a tacky solid, hardness ASTM D-1321
 (8) Minimum order quantities and extended order lead times may apply.

For additional information or to contact us, please visit: www.honeywell-additives.com

Honeywell Corporate

Headquarters

115 Tabor Road
 Morris Plains, NJ 07950
 Tech Assistance: 973-455-5382
 Customer Service: 973-455-2145
 Toll Free in U.S.:
 Tech Assistance: 800-451-9961
 Customer Service: 888-245-4738

Asia / Pacific Honeywell

No.430, Li Bing Road, Zhangjiang
 Hi-Tech Zone, Shanghai 201203
 China
 Telephone: +8621 2894-2000
 Fax: +8621 5855-3543

Europe / Middle East /

Africa / India
 Honeywell Belgium N.V.
 Gaston Geenslaan 14
 3001 Heverlee, Belgium
 Telephone: +32 16 39 12 11
 Fax: +32 16 40 00 33

Honeywell International (I) Pvt Ltd

6th Floor, Tower B, Building No. 9
 DLF Cyber City, Phase III
 Gurgaon-122002
 Haryana
 India
 Telephone: +91-124-4031361-65

All statements and information provided herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated herein, or that other measures may not be required. User assumes all liability for use of the information and results obtained.



Honeywell